

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ^S : C04B 18/08	A1	(11) International Publication Number: WO 90/11977 (43) International Publication Date: 18 October 1990 (18.10.90)
(21) International Application Number: PCT/NO90/00063 (22) International Filing Date: 9 April 1990 (09.04.90) (30) Priority data: 891463 10 April 1989 (10.04.89) NO (71) Applicant (for all designated States except US): DEN NOR-SKE STATS OLJESELSKAP A.S [NO/NO]; Forus, Postboks 300, N-4001 Stavanger (NO). (72) Inventor; and (75) Inventor/Applicant (for US only) : VASSØY, Bjørn [NO/NO]; Fagerstølveien 8, N-4027 Stavanger (NO). (74) Agent: LÆRUM, Martin; Den Norske Stats Oljeselskap a.s, Forus, Postboks 300, N-4001 Stavanger (NO).		(81) Designated States: AT (European patent), AU, BE (European patent), BR, CA, CH (European patent), DE (European patent), DK (European patent), ES (European patent), FR (European patent), GB (European patent), IT (European patent), LU (European patent), NL (European patent), SE (European patent), SU, US. Published <i>With international search report.</i> <i>In English translation (filed in Norwegian).</i>
(54) Title: PROCEDURE FOR THE ADMIXTURE OF SILICON OXIDE TO A HYDRAULIC CEMENT SLURRY (57) Abstract <p>The invention relates to a procedure for the admixture of silicon oxide to a hydraulic cement slurry, particularly for well cementing, and is characterized by amorphous silica with particles smaller than 1 micro-metre being mixed with water to a liquid micro-silica, silica flour with particles from 2 to 200 micro-metres being mixed in said liquid micro-silica and the thereby obtained silica mixture being added to cement slurry directly in a mixing tank. In addition the invention relates to a hydraulic cement slurry produced according to the procedure.</p>		

+ See back of page

RECEIVED TIME MAY. 21. 8:54AM

DESIGNATIONS OF "DE"

Until further notice, any designation of "DE" in any international application whose international filing date is prior to October 3, 1990, shall have effect in the territory of the Federal Republic of Germany with the exception of the territory of the former German Democratic Republic.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MG	Madagascar
AU	Australia	FI	Finland	ML	Mali
BB	Barbados	FR	France	MR	Mauritania
BE	Belgium	GA	Gabon	MW	Malawi
BF	Burkina Faso	GB	United Kingdom	NL	Netherlands
BG	Bulgaria	HU	Hungary	NO	Norway
BJ	Benin	IT	Italy	RO	Romania
BR	Brazil	JP	Japan	SD	Sudan
CA	Canada	KP	Democratic People's Republic of Korea	SE	Sweden
CF	Central African Republic	KR	Republic of Korea	SN	Senegal
CG	Congo	LI	Liechtenstein	SU	Soviet Union
CH	Switzerland	LK	Sri Lanka	TD	Chad
CM	Cameroon	LU	Luxembourg	TG	Togo
DE	Germany, Federal Republic of	MC	Monaco	US	United States of America
DK	Denmark				

RECEIVED TIME MAY. 21. 8:54AM

WO 90/11977

PCT/NO90/00063

PROCEDURE FOR THE ADMIXTURE OF SILICON OXIDE TO A HYDRAU-
LIC CEMENT SLURRY.

The present invention relates to a procedure for the
admixture of silicon oxide to a hydraulic cement slurry.

5

In addition, a hydraulic cement slurry produced according to
said procedure.

This type of hydraulic cement slurry is primarily used in
10 hydrocarbon wells and in geo-thermal wells.

Cement slurries with silicon oxide admixture are typically
used in oil well cement where their primary purpose is to
prevent reduction of cement slurry strength over time,
15 particularly at high pressure and temperatures exceeding
100°C.

In connection with primary cementing of hydrocarbon wells,
cement slurries are pumped down through casings in the well,
20 and up on the outside, filling the annulus between the
casing and borehole wall. The major purposes of the
cementing are:

- 1) Support and protect the casing.
- 25 2) Isolate weak structures or high-pressure zones.
- 3) Prevent water, oil or gas from moving between
structures or up to the surface.

BACKGROUND ART

30

When exposed to temperatures above 100°C over an extended
period, an ordinary cement slurry used in hydrocarbon wells
will gradually lose its pressure strength at the same time
as its permeability increases. These properties increase
35 with increasing temperature.

At temperatures above 130°C, this may occur after just 24
hours. This may develop to a stage where the cement crumbles
and thus loses its function.

RECEIVED TIME MAY. 21. 8:54AM

WO 90/11977

PCT/NO90/00063

2

At temperatures above 100°C, the ordinary C-S-H (calcium-silicate-hydrate) binding turns to alpha-calcium-silicate-hydrate. Thus, the strength is reduced, and the permeability increases.

5

In order to prevent this reaction, it is normal to add SiO₂, silicon oxide, in the cement slurry. SiO₂ prevents the formation of alpha-calcium-silicate-hydrate. Instead, mono-calcium-silicate-hydrate is formed, which is a more stable binding. Thus, the strength is maintained. The most common way of adding the cement slurry SiO₂ is to add silica flour and silica sand. Both substances mainly consist of SiO₂.

15 Silica flour is a light grey/white powder produced from quarts. It is produced both in Europe and the U.S., and has a number of product names such as "SSA-1" from Halliburton Services, "D-66" from Dowell Schlumberger or "D-8" from B.J. Hughes. The specific weight is approx. 2.63 gcm⁻³. The grain size is between 2 and 200 micro-metres, approx. 50 weight% being less than 50 micro-metres. This is more or less the same grain size as oil well cement.

The silica sand is much more coarse-grained than silica flour. The size of the grains is usually from 1 to 2 mm. Also silica sand is produced from quarts and has a specific weight of approx. 2.63 gcm⁻³.

Silica flour is definitely the most common of these. In order to prevent strength reduction in the cement slurry, minimum 35 % silica flour must be used based on the weight of cement.

This silica flour is today mixed dry with the dry cement in silos onshore. This is done by blowing each dry substance with pressurized air from its respective silo into a third silo. Subsequently, the mixture is blown back and forth between two silos. This results in a somewhat homogeneous

WO 90/11977

PCT/NO90/00063

3

mixture. This blowing, however, deteriorates the properties of the finished cement slurry since the pressurized air contains small amounts of water. The properties that are deteriorated are: free water is increased, the filter loss increases and the setting time increases. These properties are all critical to a cement slurry.

With this mixing method, it is very difficult to get an accurate dosaging of the various components. This is due to the fact that measuring accurate amounts of dry substances represents a measurement-technical problem. In addition, there are problems obtaining a homogeneous and stable mixture.

The prior art also requires separate storage silos on the rigs for the storage of the dry mixture. This may in many cases involve problems due to poor silo capacity. In addition, so much dry mixture is mixed that there is enough for two jobs (100 % backup). What remains after the cementing job is done, is usually used in cement slurries that do not require such silica flour. The objective of this is to rid of the mixture, thus making the storage silo available for ordinary cement. This is rather unfavourable from an economic point of view.

Recently, it has been realized that the admixture of micro-silica also prevents reduction of strength at high temperatures. Micro-silica reacts the same way as silica flour in a cement slurry exposed to high temperatures. Also here, mono-calcium-silicate-hydrate is formed.

Silica dust collected from electro-thermal melting furnaces that produce at least 75 % ferrosilicon (Si contains at least 76 %) is preferably used as micro-silica, but dust from furnaces that produce 50 % ferrosilicon may also be used as a basis material for the present invention.

WO 90/11977

PCT/NO90/00063

4

It is also possible to obtain silicon dust as a main product from the said melting furnaces by adjusting the reduction conditions. This type of amorphous silica can also be synthetically produced without reduction and re-oxidation. 5 Alternatively, a silica dust generator can be used for the production of silica fines, or silica may be produced by precipitation.

In order for micro-silica to be easily transportable, the 10 producer mixes it with approx. 50 weight% of fresh water. A liquid micro-silica with a specific weight of approx. 1.40 gcm⁻³ is then obtained. Elkem has e.g. given this mixture the product name "EMSAC 460S".

15 According to a known method, the cement slurry density must be reduced from approx. 1.90 gcc to approx. 1.70 gcc in order to add a sufficient amount of liquid micro-silica.

Subsequently, the mixture must be weighed up again to the 20 desired density by means of weight materials. This is an inconvenient solution, even more serious, however, is the fact that this method gives a too viscous and thixotropic cement slurry.

25 The ph of the mixture is increased by another known method prior to adding all of the cement, thus allowing 35 % micro-silica to be added. Consequently, the tiny micro-silica particles flocculate, and this gives a non-gas-tight cement slurry. In addition, also this method 30 gives a too viscous and thixotropic cement slurry.

Object of the invention

The purpose of the present invention is to provide an 35 improved procedure for the admixture of silicon oxide where the above-mentioned problems are overcome.

WO 90/11977

PCT/NO90/00063

5

THE PRESENT INVENTION

This, according to the present invention, is obtained by a procedure characterized by:

5

- amorphous silica with particles of less than 1 micro-metre being mixed with water to liquid micro-silica,
- silica flour with particles from 2 to 200 micro-metres
10 being mixed in the liquid micro-silica and the thereby obtained silica mixture being added to a cement slurry directly in a mixing tank.

The invention also includes a hydraulic cement slurry which
15 contains 5 - 100 % silicon oxide additive containing liquid amorphous silica with particles of less than 1 micro-metre with a silica flour admixture, based on the weight of cement, 2 - 200 % light weight aggregate with a particle density of between 0.1 and 1.5 g/cm³, based on the weight of
20 cement, 0 - 5 % thinner (dry weight) based on the weight of cement, 1 - 10 % filter loss reducing agent (dry weight) based on the weight of cement, and water of such an amount that the cement slurry gets a density of between 0.8 and 2.0 g/cm³.

25

The amorphous silica dust used in the present invention mainly consists of submicron globular particles.

The silica dust particles may e.g. contain 60 - 100 weight%
30 of SiO₂ and have a density of 2.0 - 2.40 g/cm³ and a specific surface area of 15 - 30 m²/g. The particles are mainly globular and are less than 1 micro-metre in size. These values may of course vary. For example, the silica dust may have a lower SiO₂ content and the particle size
35 distribution may be adjusted, e.g. by coarse particles being removed.

WO 90/11977

PCT/NO90/00063

6

Silica flour and liquid micro-silica are mixed so that the total of the two substances represents minimum 35 weight% of dry substance of the dry cement weight in a cement slurry. Thus, a reduction of strength at high temperature is prevented. The mixture of the 2 substances also gives good cement slurry properties, such as very low viscosity, minimal thixotropic properties, stable slurry, low filter loss and zero free water. In addition, slurries which contain more than a given amount of micro-silica have gas-tight properties.

The mixture of the two substances may be done onshore in a mixing plant. Since liquid micro-silica is one of the components, it can be measured with great accuracy. The silica flour is added in the liquid micro-silica until the desired density of the finished mixture is obtained. This gives an accurately composed mixture.

Other advantages of the invention:

20

- The mixture is entirely stable, even after several months' storage.
 - The mixture pumpability is good and it may be added directly in a pre-mixing tank on rigs or directly in the mixing tanks on cement mixing units.
 - Extra blowing of dry cement and silica flour from one silo to another is avoided.
 - The mixture does not require a special storage tank on the rigs.
- 30 - Excessive amounts of the mixture can be returned onshore and stored for later use.

MODES FOR CARRYING OUT THE INVENTION

35 The invention will now be further described by means of the following examples.

WO 90/11977

PCT/NO90/00063

7

Example 1

A silica mixture with the following composition was produced according to the present invention:

5

Silica flour, "SSA-1"	55.6 weight%
Micro-silica (50% dry substance)	44.4 weight%

The silica flour is "SSA-1" delivered by Halliburton
10 Services, Tananger. Micro-silica is "EMSAC 460S" from
Elkem, Bremanger Smelteverk (50 weight% of dry substance in
water).

The rheologic properties at 20°C were:

15 600rpm = 210cp, 300rpm = 126cp, 200rpm = 94cp, 100rpm =
53cp.

The mixture of silica flour and liquid micro-silica may
contain 5-80 weight% of silica flour, preferably 40-60
20 weight%, and 20-95 weight% of liquid micro-silica,
preferably 40-60 weight%.

In addition, all types of weight materials, dispersants,
retarders, accelerators, filter loss reducing substances,
25 weight-reducing substances and anti-foam agents may be added
to mixtures of silica flour in liquid micro-silica.

All types of materials used in oil well cement may be used
as weight materials, preferably hematite, ilmenite or
30 barite. The mixture may possibly contain 0-50 weight% of
weight material, chiefly 0-20 weight%.

All such agents known to be used as plasticizing, or super-
plasticizing, agents in cement-based systems may be used as
35 dispersants. For example agents based on lignosulfonates,
partly de-sulfonated lignosulfonates, polyhydroxyl-carboxyl
acids, sulfonated naphthalene-formaldehyde - or sulfonated
melamine-formaldehyde products.

WO 90/11977

PCT/NO90/00063

8

The mixture may possibly contain 0-10 weight% of dispersant (based on dry substance), chiefly 0-2 weight%.

The mixture according to the present invention may contain 5 retarders such as cellulose derivates, sugar derivates, ligno-sulfonates and lignins.

The mixture may possibly contain 0-10 weight% of retarder based on dry substance, preferably 0-2 weight%.

10

Sodium chloride (NaCl) and calcium chloride (CaCl_2) may be used as accelerator.

The mixture may possibly also contain 0-10 weight 15 accelerator, preferably 0-2 weight%.

The mixture according to the present invention may contain filter loss reducing agents, e.g. agents based on amyl or amyl derivates, cellulose derivates such as carboxyl-ethyl- 20 cellulose, methyl-cellulose or ethyl-cellulose, or synthetic polymers such as polyacrylonitrile or polyacrylamide.

The mixture may possibly contain 0-10 weight% of filter loss reducing agent (based on dry weight), preferably 0-2 25 weight%.

Hollow glass balls are particularly preferred as weight-reducing agents. This type of light weight aggregate is available under a number of product names, e.g. hollow glass 30 balls produced by 3M Company, the U.S.

Also whole balls produced from shifting ashes may be used, e.g. the product "Fillite" produced by Fillite Ltd., England.

35

The mixture may possibly contain 0-50 weight% of weight reducing substances, preferably 0-30 weight%.

WO 90/11977

PCT/NO90/00063

9

According to the present invention, fresh water or sea-water may be used as water. The mixture may possibly contain 0-50 weight% of water, preferably 0-20 weight%.

- 5 The mixture may be used in cement slurries based on all types of oil well cement described in API SPEC 10.

Example 2

- 10 A typical cement slurry where the silicon oxide mixture described above in this example is included:

Norcem G-cement	100 kg
Silica flour	25 kg
15 Micro-silica, 50% dry substance	20 kg
Filter loss reducing agent	7 l
Dispersant	0.5 kg
Retarder	0.97 kg
Fresh water	36.59 l

20

This cement slurry had the following characteristics:

Density:	1.90 g/cm ³
25 Silica flour, "SSA-1"	55.6 weight%
Micro-silica (50% dry substance)	44.4 weight%

The plastic viscosity was 84 cp, and the yield strength was 20.16 Pa.

30

The rheologic properties at 90°C:

300 rpm: 23 cp, 200 rpm: 17 cp, 100 rpm: 10 cp, 6 rpm: 1 cp.

35 API SPEC 10 filter loss: 34 cm³/30 min.

Pressure strength after 24 hours at 124°C: 216 bars.

WO 90/11977

PCT/NO90/00063

10

Example 3

In order to compare the pressure strength of a cement slurry containing the silicon oxide mixture according to the present invention with a slurry according to known technology, two cement slurries, 1 and 2, with the following composition may be referred to:

Slurry 1: (According to known technology).

10

G-cement	100.0 kg
Liquid micro-silica	11.0 kg
Filter loss reducing substance	0.5 kg
Dispersant	3.0 l
15 Retarder	0.27 l
Anti-foam agent	0.20 l
Fresh water	36.40 l

The density of the slurry: 1.90 g/cm^3 .

20

Slurry 2: (according to the invention).

G-cement	100.0 kg
Silica flour	25.0 kg
25 Liquid micro-silica (50% dry substance)	41.7 kg
Filter loss reducing substance	10 l
Dispersant	0.5 kg
Retarder	0.4 kg
Anti-foam agent	0.2 l
30 Fresh water	78.86 l

The density of the slurry: 1.60 g/cm^3 .

The development of the pressure strength over time at 134°C was measured with an "Ultrasonic Cement Analyzer" (UCA), and the results are given in the table below:

WO 90/11977

PCT/NO90/00063

11

Slurry UCA pressure strength at 134°C (bar)								
no.	0.5 dg	1 dg	2 dg	3 dg	5 dg	7 dg	14 dg	28 dg
1	145	155	152	138	117	103	56	-
5 2	55	93	103	105	107	110	110	110

Slurry no. 2 gets lower pressure strength than no. 1 at the beginning due to lower specific weight of the slurry.

WO 90/11977

PCT/NO90/00063

12

CLAIMS

1. Procedure for the admixture of silicon oxide to a hydraulic cement slurry, particularly for well cementing, characterized by
 - amorphous silica with particles smaller than 1 micro-metre being mixed with water to a liquid micro-silica,
 - silica flour with particles from 2 to 200 micro-metres being mixed in said liquid micro-silica,
 - the thereby obtained silica mixture being added to cement slurry directly in a mixing tank.
2. Procedure according to claim 1, characterized by 5 to 80 weight% of silica flour being added, preferably from 40 to 60 weight%, from 95 to 20 weight% of liquid micro-silica, preferably from 60 to 40 weight% based on the weight of dry substances, and from 0 to 50 weight% of water, preferably below 20 weight% based on the weight of dry substances, where the water may be fresh water or sea-water.
3. Procedure according to claims 1 and 2 characterized by said silica flour and micro-silica together representing 35 weight% of the cement on the basis of dry substances in a cement slurry.
4. Hydraulic cement slurry for oil well cementing characterized by that it contains hydraulic cement, 5 - 100 % silicon oxide containing liquid amorphous silica with particles smaller than 1 micro-metre and with a silica flour admixture based on the weight of cement, 2 - 200 % light weight aggregate with a true particle density of between 0.1 and 1.5 g/cm³, based on the weight of cement, 0 - 5 %

WO 90/11977

PCT/NO90/00063

13

5 thinner (dry weight) based on the weight of cement, 1 -
10 % filter loss reducing agent (dry weight) based on
the weight of cement, and water of such an amount that
the cement slurry gets a density of between 0.8 and 2.0
g/cm³.

10 5. Hydraulic cement slurry according to claim 4,
c h a r a c t e r i z e d b y this being produced
according to the procedure stated in claims 1-3.

INTERNATIONAL SEARCH REPORT

International Application No PCT/NO 90/00063

I. CLASSIFICATION OF SUBJECT MATTER (If several classification symbols apply, indicate all) ⁶		
According to International Patent Classification (IPC) or to both National Classification and IPC		
IPC5: C 04 B 18/08		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
IPC5	C 04 B	
Documentation Searched other than Minimum Documentation to the extent that such documents are included in Fields Searched ⁸		
SE,DK,FI,NO classes as above		
III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹		
Category ¹⁰	Citation of Document ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
A	EP, A2, 0146912 (BIURO STUDIOW I PROJEKTOW ENERGETYCZNYCH "ENERGOPROJEKT") 3 July 1985, see the whole document --	1-5
A	NO, B, 148995 (ELKEM A/S) 17 October 1983, see the whole document --	1-5
A	DE, A1, 3522677 (HEINRICH ELSKES KG) 8 January 1987, see the whole document -- -----	1-5
<p>* Special categories of cited documents:¹⁰</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"T" document published prior to the international filing date but later than the priority date claimed</p> <p>"X" document of particular relevance, the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance, the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"A" document member of the same patent family</p>		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	
9th July 1990	1990-07-10	
International Searching Authority	Signature of Authorized Officer	
SWEDISH PATENT OFFICE	May Hallne <i>May Hallne</i>	

Form PCT/ISA/210 (second sheet) (January 1985)

RECEIVED TIME MAY. 21. 8:54AM

**ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO.PCT/NO 90/00063**

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.
The members are as contained in the Swedish Patent Office EDP file on 90-05-24
The Swedish Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A2- 0146912	85-07-03	JP-A- 60227818 US-A- 4618376	85-11-13 86-10-21
NO-B- 148995	83-10-17	NONE	
DE-A1- 3522677	87-01-08	NONE	

RECEIVED TIME MAY. 21. 8:54AM